

<b>Subject:</b>	<b>VISUAL ASSESSMENT AFTER FLORIDA EXPOSURE</b>
<b>Proposal:</b>	<b>QUALISURFAL</b> The Florida working group's visual assessment of powders of gloss category 1 should be included in the Specifications. <b>POWDERS working group</b> The visual assessment of structural systems in all categories and of special colours with a metallic effect should also be included in the Specifications.
<b>QUALICOAT resolution:</b>	<b>Meeting held on 21 November 2007</b> <i>(ratified on 26 June 2008)</i>
<b>Date of application:</b>	<b>July 2008</b>
<b>Amendments to the Specifications:</b>	<b>Section 2.13 Natural weathering test</b>

## 2.13 Natural weathering test

[...]

### REQUIREMENTS:

#### Gloss

**The residual gloss must be at least 50% of the original gloss.**

An additional visual assessment will be carried out by QUALICOAT for

- coating systems of gloss category 1 where the residual gloss is less than 50%;
- structural systems in all gloss categories;
- special colours with a metallic effect.

[...]