

<b>Subject:</b>	<b>CLARIFICATION REGARDING STRUCTURED POWDERS</b>
<b>Proposal:</b>	<b>“Florida” Working Group (11.06.09):</b> It should be specified that structured systems have to be tested on the same basic colours as standard powders.
<b>QUALICOAT resolution:</b>	<b>TC/EC Meeting held on 19 November 2009</b> <i>(ratification on 23 June 2010)</i>
<b>Date of application:</b>	<b>1 September 2010</b>
<b>Amendments to the Specifications:</b>	4.1.2

#### 4.1.2 Tests for granting an approval

[...]

The tests must be made on three test panels (for mechanical tests) and on three sections (for corrosion tests) coated by a laboratory approved by the Executive Committee. The average of the three samples will be taken to determine the results.

For class 1 and class 2 the following colours must be tested (independently of gloss category or finish):

- white RAL 9010
- blue RAL 5010
- red RAL 3005

plus a metallic colour (see Appendix A4)

[...]