



recommendations for the  
**care of coated aluminium**



**architectural** coatings







the

# **global** **standard** for **architectural** **aluminium** **finishing**

## recommendations for the care of coated aluminium

These recommendations cover procedures for cleaning and maintenance of painted aluminium extrusions and curtain wall panels. The procedures are intended for use with powder coated, architectural and aluminium extrusions such as window frames, door frames, railings and trim as well as curtain wall panels, column covers, spandrels, mullions, louvres, vertical trim, etc.

These recommendations are intended to assist architects, contractors, owners and building managers who are concerned with the care and maintenance of painted, architectural aluminium. The information contains suggested methods as an aid in establishing safe, sound cleaning and maintenance procedures.

# recommendations

## Technical Information Sheet 1

July 2011 Edition

Care of coated aluminium not only refers to cleaning and maintenance of the surface but also covers all other operations that may have detrimental effects on the surface, for instance transport, packaging, installation and so on.

Care should start immediately. Organic coating can suffer mechanical damage, like scratches on the surface, especially on some colours.

Recommendations will be given for the following steps:

1. Handling and transportation
2. Installation
3. Cleaning
4. Special finish
5. Cleaning frequency
6. Damage repair
7. Other recommendations

### 1. Handling and Transport

- a. The coated aluminium should be protected during handling to avoid mechanical damage.
- b. Suitable protective materials should be used for packaging and transportation (to avoid water spots caused by the greenhouse effect).
- c. Packaging should be securely fixed.

### 2. Installation

- d. During storage, the coated aluminium should be protected from the influence of weather elements and therefore stored out of direct sunlight, rain and other weather elements (sheltered storage).
- e. On the construction site and during construction, the coated aluminium should be protected from damage caused by abrasion and construction materials, such as paint, mortar, cleaning chemicals etc.
- f. If such materials have been in contact with the coated surface, they should be cleaned immediately before they have dried. Failure to remove these materials at this early stage will require the use of aggressive cleaning materials and techniques that may result in damage to the coated surface.

### 3. Cleaning

- g. It is strongly recommended to first test a small, inconspicuous test area to ensure that no colour change or damage arises.
- h. Always remove any kind of dirt as soon as possible.
- i. If, for acceptance of construction work, any loose deposits still remain

despite cleaning during installation, they must be removed with a wet sponge (water).

- j. If it is not possible to clean the surface as described above, use a soft brush or (non-abrasive) cloth and a neutral mild household or neutral car wash detergent, following the supplier's instructions.
- k. After cleaning, rinse the surface thoroughly with fresh water.
- l. Do not use steel wool, scrapers, sandpaper, scouring liquids or powders as they will permanently scratch the coated surface.
- m. Do not use strong solvents alkaline or acid cleaners.
- n. The use of hard water for cleaning is not recommended due to its mineral content, as it can cause staining of the coating and may lead to long-term failures.
- o. Do not clean the surface if it is hot due to being in direct sunlight.

## 4. Cleaning of Special Finishes

- p. Metallic coatings contain mica or metallic flakes. Special care must be taken when cleaning this kind of special finish. For routine cleaning, periodic washing with mild detergent is recommended. Any cleaning or repair by rubbing or polishing must be avoided as it may result in discolouration, colour change and irreversible damage to the coating.
- q. Matt finishes: for cleaning, washing with a mild detergent is recommended. If repair or restoration is required, rubbing or polishing should be avoided since the gloss level of the coating could be affected.

## 5. Cleaning Frequency

- r. As a general rule, the coated surface should be cleaned at least once a year in a normal environment. However in areas where pollutants are more prevalent, especially in coastal or industrial areas, a more frequent cleaning programme should be carried out.

**Normal environment** - Clean every 12 months

**Marine and/or industrial environment** - Clean every 3 months

**Swimming & leisure pools** - Clean every 3 months

## 6. Damage Repair

- s. Depending on the damage, different kinds of repair may be necessary. The coating suppliers must be contacted to find the best solution.

## 7. Other Recommendations

- t. Cleaning should be carried out by specialised cleaning companies.



**AAG NPC**  
Greece



#### Aluminium Association of Greece

A41-43 Michalakopoulou str.  
GR-115 28 Athens

TEL +30 210 72 56 130-2  
WEBSITE [www.aluminium.org.gr](http://www.aluminium.org.gr)



**AYID**  
Turkey



#### Alüminyum Yüzey İşlem Derneği

Şemsettin Gülnaltay Caddesi Serhan Apt.  
193/5, Erenköy - Kadıköy  
TR - 34738 İstanbul

TEL +90 216 386 16 85  
WEBSITE [www.ayid.org.tr](http://www.ayid.org.tr)



**AEA**  
Spain



#### Asociación Española del Aluminio y Tratamientos de Superficie

Príncipe de Vergara, 74 – 3ª  
ES - 28006 Madrid

TEL +34 914 112 791  
WEBSITE [www.asoc-aluminio.es](http://www.asoc-aluminio.es)



**QUALICOAT  
FRANCE**  
France



#### QUALICOAT France

17 rue de l'amiral Hamelin  
FR - 75116 Paris

TEL +33 01 42 25 26 44  
WEBSITE [www.qualicoat.fr](http://www.qualicoat.fr)



**AFMSZ**  
Hungary



#### Hungarian Aluminium Surface Treaters' Association

Népfürdő u. 19/A. I/4.  
HU - 1138 Budapest

TEL +36 30 9590575  
WEBSITE [www.afmsz.hu](http://www.afmsz.hu)



**QUALICOAT  
Japan**  
Japan



#### c/o Japan Aluminium Products Association

13-13 Akasaka 2-chrome, Minatoku  
JP - Tokyo

TEL +81 3 3583 7971  
WEBSITE [www.apajapan.org/QCJ/info.html](http://www.apajapan.org/QCJ/info.html)



**AMELAQ**  
Mexico



#### AMELAQ

Francisco I. Madero 146  
San Esteban, Naucalpan MX - 53550  
Estado de Mexico

TEL +52 555 1083-5092  
WEBSITE [www.amelaq.org](http://www.amelaq.org)



**QUALICOAT Schweiz**  
Switzerland



#### QUALICOAT Schweiz

Tödistr. 42  
Postfach  
CH - 8027 Zürich

TEL +41 43 305 09 81  
WEBSITE [www.qualicoat.ch](http://www.qualicoat.ch)



**APAL**  
Portugal



#### APAL - Associação Portuguesa do Alumínio

R. Cons. Luís de Magalhães  
N.º 46-1.º Andar- Sala B-2  
Apartado 287  
PT - 3811-901 Aveiro

TEL +351 234 42 22 41  
WEBSITE [www.apal.pt](http://www.apal.pt)



**QUALICOAT UK  
& Ireland**  
UK & Ireland



#### QUALICOAT UK & Ireland c/o Aluminium Federation Ltd.

Bragborough Hall Business Centre,  
Welton Road, Braunston, Daventry,  
Northamptonshire NN11 7JG

TEL +44 (0) 333 240 9735  
WEBSITE [www.qualicoatuki.org](http://www.qualicoatuki.org)



**QUALIPOL**  
Poland



#### QUALIPOL

Stowarzyszenie Wykonawców Obróbki Powierzchni  
Metalowych ul. Sępa 22  
PL-04-512 Warsaw

TEL +48 500 579 089  
WEBSITE [www.qualipol.pl](http://www.qualipol.pl)



**QUALI MIDDLE EAST**  
Bahrain, Egypt, Kuwait, Oman, Qatar,  
Saudi Arabia, United Arab Emirates



#### QUALI MIDDLE EAST ASSOCIATION

c/o Dubai Association Center  
Office No. 207 (16), Level 2, Building 2 at One Central  
Dubai World Trade Centre  
P.O. Box 23070, Dubai-UAE

TEL +971 4 516 3052  
WEBSITE [www.qualimiddleeast.com](http://www.qualimiddleeast.com)



**QUALISINO**  
CHINA



#### QUALISINO

Room 501, Building 25, 189 Hongcan Road  
Xiaoshan Economic & Technological  
Development Zone  
CN - 311232 Hangzhou City, P.R. China

TEL +86 571 8286 5811  
WEBSITE [www.qualisino.com](http://www.qualisino.com)



**VOA**  
Germany



#### Verband für die Oberflächenveredelung von Aluminium e.V.

Max-Joseph-Str. 5  
DE - 80333 München

TEL +49 (0) 89 55 17 86 70  
WEBSITE [www.voa.de](http://www.voa.de)



**QUALITAL**  
Italy



#### QUALITAL - ISTITUTO DI CERTIFICAZIONE INDUSTRIALE DELL'ALLUMINIO E ALTRI MATERIALI

Strada Priv. Ragni Meloni, 13/15  
IT - 28062 Cameri (No)

TEL +39 0321 1828 222  
WEBSITE [www.qualital.eu](http://www.qualital.eu)



**QUALUBEL**  
Belgium



#### QUALUBEL

Chemin des Soeurs 7 Nodebais  
BE - 1320 Beauvechain

TEL +32 473 451 263 (MOBILE)  
WEBSITE [www.qualubel.be](http://www.qualubel.be)



**Qual.ION**  
Netherlands



#### Vereniging Qual.ION

Postbus 2600  
NL - 3430 GA Nieuwegein

TEL +31 30 630 03 90  
WEBSITE [www.vereniging-ion.nl/qualion](http://www.vereniging-ion.nl/qualion)

the **global**  
standard for architectural  
**aluminium** coatings

**QUALICOAT**  
Certification Body

**OFFICE:**

Tödistrasse 48  
CH-8002 Zurich

**TEL:** +41 44 515 98 40



**Accreditation:**

QUALICOAT Tödistrasse 48  
CH-8002 Zurich

**GENERAL INFORMATION**

[info@qualicoat.net](mailto:info@qualicoat.net)

**ACCOUNTING**

[accounting@qualicoat.net](mailto:accounting@qualicoat.net)

**QUALIDECO**

[qdc@qualicoat.net](mailto:qdc@qualicoat.net)

**COATERS**

[coaters@qualicoat.net](mailto:coaters@qualicoat.net)

**POWDERS**

[powders@qualicoat.net](mailto:powders@qualicoat.net)

**PRETREATMENT**

[pretreatment@qualicoat.net](mailto:pretreatment@qualicoat.net)

[www.qualicoat.net](http://www.qualicoat.net)



the **global** standard for architectural **aluminium** coatings